

TIMBER DECKING

| | CLASS DURABILITY (ABOVE GROUND) | CLASS DURABILITY (IN-GROUND) | DENSITY | EXTERNAL LIFE ABOVE GROUND |
|---|--|---|----------------------------|---------------------------------------|
| KD Ironbark | 1 | 1 | 1130kg / m ³ | More than 25 years |
| KD Forest Red Gum | 1 | 1 | 1050kg / m ³ | More than 25 years |
| KD Spotted Gum | 2 | 2 | 960kg / m ³ | 15 - 25 years |
| KD Yellow Stringybark | 2 | 3 | 870kg / m ³ | 15 - 25 years |
| KD Blackbutt | 2 | 2 | 900kg / m ³ | 15 - 25 years |
| KD Silvertop Ash | 2 | 3 | 830kg / m ³ | 15 - 25 years |
| Recycled Stringybark (mixed species) | 2-3 | 3 | 830-900kg / m ³ | 15 years * |

* treated with decking oil